

#42 BULLDOG® NON-FIBERED EMULSION DAMPPROOFING



DESCRIPTION

A brush or spray grade asphaltic coating emulsified with water and agents. SPECIFICATIONS: ASTM D 1227, TYPE III, CLASS I and ASTM D 1187, TYPE I

USES

Used to dampproof exterior masonry surfaces below grade in situations where a heavy coating is not required. This material will adhere to new, or "green", slightly damp surfaces.

METHODS AND RATE OF APPLICATION

Apply by brush or spray to slightly damp surface at rate of 2 ½ gallons per 100 square feet (1 liter per M²). Apply at 50°F and rising. Wait 48 hours before backfilling when applied below grade.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	520 POUNDS
5 Gallon Pail	46 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

% Solids by Weight	50.0
Water Content, % by Weight	50.0
Net Weight Per Gallon, Pounds	8.6
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon.....	8 Mills
Dry Time @ Recommended Rate of Application	24 Hours
Accelerated Weathering.....	No Cracking, No Alligating, No Sagging
Resistance to Water, Cured Film	No Blistering, No Reemulsification
Condition in Container	May Require Slight Stirring
Storage Precautions.....	Keep From Freezing
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE(201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com