

#603 BULLDOG® NON-FIBERED DAMPPROOFING



DESCRIPTION

An easily applied liquid coating made with select asphalts and petroleum solvents.

USES

Used in dampproofing applications where a heavy compound is not required and where no reinforcing membrane is intended to be used. Used to dampproof exterior surfaces below grade. This product demonstrates excellent adhesion when applied to concrete, masonry and steel surfaces.

METHODS AND RATE OF APPLICATION

Apply by brush or spray to clean, dry surface at rate of one gallon per 100 square feet. (.4 liters per M²). COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING. Wait 48 hours before backfilling when applied below grade.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drums	520 POUNDS
5 Gallon Pail	46 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight	73.0
Volatile Solvent, % by Weight	27.0
Asphalt Solids, % by Volume	73.0
Water Content, % by Volume	0.0
Net Weight Per Gallon, Pounds	7.8 lbs.
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon9 Mills
Dry Time @ Recommended Rate of Application	1 Day
Service Temperature	-30°F to +160°F
Flash Point, in Degrees F., C.C., ASTM D 93	103 Minimum
Finish	Hard, Glossy
Condition in Container	Homogeneous
Clean Up of Tools	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE (201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com