

#109AF BULLDOG® ASPHALT ROOF RESATURANT



DESCRIPTION

A non-asbestos fibered black asphalt compound enhanced by penetrants that help it rejuvenate badly deteriorating asphalt roofs. Part of this compound soaks into dried out roofing felts and part of it remains on the surface to provide water/weather-proof protection.

USES

Use when asphalt felts have dried as a result of unprotected exposure to sun's destructive rays. Used to restore roof, rather than remove. This extends the life of the in place asphalt roof and reduces cost by eliminating the need for roof tear off and reduces waste. All areas of roof that may contain wet roof insulation should be removed and replaced with like material

METHODS AND RATE OF APPLICATION

Apply with roof brush, roller or spray equipment to dry, sound, clean surface. Remove loose gravel. Depending on condition of surface, apply at rate of 4 to 7 gallons per 100 square feet (1.6 to 2.8 liters per M²). If removing existing gravel is desired do so with power brush or other suitable means that will not damage underlying felts. If gravel is to be reused power wash before reusing to remove silt. Reapply gravel at rate of 400 pounds per 100 square feet immediately after applying Resaturant. Be certain roof can support additional weight. DO NOT THIN. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	490 POUNDS
5 Gallon Pail	43 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight	70.5
Volatile Solvent, % by Weight	29.0
Fillers and Fibers, % by Weight	9.0
Asphalt Solids, % by Volume.....	63.0
Water Content, % by Volume	0.5
Net Weight Per Gallon, Pounds	8.3
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon.....	9 Mills
Dry Time @ Recommended Rate of Application	2-3 Days
Service Temperature	-30°F to +150°F
Flash Point, in Degrees F., C.C., ASTM D 93	104
Condition in Container	May require slight stirring
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE(201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com