

#76AF BULLDOG® PLASTIC ROOF CEMENT



DESCRIPTION

A high grade trowel consistency compound prepared with asphalt, petroleum spirits, and select mineral fillers. It expands and contracts with changes in temperature and building surfaces without loss of adhesion. Bonds securely to many surfaces and will not sag on horizontal or vertical surfaces. Seasonally formulated for ease of application. SPECIFICATIONS: ASTM D 4586, TYPE I, CLASS I

USES

Use for filling in worn, cracked spots, and holes in roofs and around skylights, chimneys, and gutters on all flashings. Also for heavy duty foundation waterproofing, pointing up brick and stone work, and patching truck and trailer roofs. May be used with a variety of built-up roofing materials. Effective in stopping leaks.

METHODS AND RATE OF APPLICATION

Use a trowel to apply to clean dry surface. Apply approximately 1/8 inch (3.2mm) thickness. One gallon (3.78 liters) will cover 13 square feet (1.2 square meters). For repairing cracks, splits, and blisters on built-up roofing use in conjunction with BULLDOG Asphalt Saturated Cotton Fabric Polyester Fabric. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	512 POUNDS
5 Gallon Pail	46 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight.....	76.0
Volatile Solvent, % by Weight.....	24.0
Mineral Filler and/or other Stabilizers, % by Weight.....	18.0
Asphalt Solids, % by Volume.....	60.0
Water Content, % by Volume.....	0.5
Net Weight Per Gallon, Pounds	8.7
Dry Film Thickness Without Absorption Applied at Rate of 13 Square Feet Per Gallon.....	77 Mils
Dry Time @ Recommended Rate of Application	3 Days - Outside Shell
Service Temperature	-30°F to +150°F
Behavior @ 60°C., ASTM D 4586.....	No Sagging, No Blistering
Behavior @ 0°C., ASTM D 4586	No Cracking, No Separation
Flash Point, in Degrees F, C.C., ASTM D 93	104
Condition in Container	Homogeneous
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE(201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com