

#79AF BULLDOG® SECUREFLASH® RUBBERIZED FLASHING CEMENT FOR WET OR DRY SURFACES



DESCRIPTION

BULLDOG SECUREFLASH is a chemically modified roof flashing cement reinforced with select polymers. SECUREFLASH contains a trade secret ingredient that allows this product to provide superior adhesion to wet surfaces when tested in accordance with ASTM D3409. This product contains significant polymers that provide an unusually high percentage of elongation and recovery. SPECIFICATIONS: ASTM D 4586, TYPE I, CLASS I and II

USES

BULLDOG SECUREFLASH is a multipurpose roof cement that can be used to repair leaks on asphalt and metal surfaces, repair and adhere SBS modified bitumen membranes, repair cracks in flashings, prevent leaks around roof protrusions and can be used as a shingle tab cement. Not intended to be used on coal tar and EPDM and other single ply roofs.

METHODS AND RATE OF APPLICATION

After removing all loose dirt, grease, or oils apply uniformly by trowel to dry surfaces at rate of 1/8" to 1/4" thick. Apply to wet surface at rate of 1/4" thick or heavier, if needed to stop leak. Use pressure to insure a firm bond. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
3 Gallon Pail	28 POUNDS
5 Gallon Pail	46 POUNDS
Cartridges (6 to Carton)	5 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight.....	75
Volatile Solvent, % by Weight.....	25
Mineral Filler and/or other Stabilizers, % by Weight.....	20
Water Content, % by Volume.....	0.05
Net Weight Per Gallon.....	8.5
Dry Film Thickness Without Absorption Applied at Rate of 13 Square Feet Per Gallon.....	77 MILS
Dry Time @ Recommended Rate of Application.....	2 Days - Outside Shell
Service Temperature.....	-30°F to +150°F
Behavior @ 60°C., ASTM D 4586.....	No Sagging, No Blistering
Behavior @ 0°C., ASTM D 4586.....	No Cracking, No Separation
Flash Point, in Degrees F., C.C., ASTM D 93.....	104 Minimum
Condition in Container.....	Homogeneous
Elongation @ 73° F, %.....	270 Minimum
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES. The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
196 WEST 5TH ST
P.O. BOX 58
BAYONNE, NJ 07002
PHONE (201) 339-0855
FAX (201) 339-8320
www.palmerasphalt.com