

#94AF BULLDOG® RED CEMENT



DESCRIPTION

BULLDOG Red Cement combines a special formulation of a high grade asphalt, solvents, pigment, and fibers and fillers carefully blended to produce a smooth consistency trowel grade cement that will adhere well to the surface being treated.

USES

Use BULLDOG Red Cement where a dark colored, heavy duty mastic with exceptional adhesion and quick drying capabilities is required. Designed for use in dampproofing exterior walls and parapets. Can be used for bedding quarry tiles, slate roof repairs, and pointing up around copper and brick work. Often used in historical restoration and around chimneys and masonry surfaces

METHODS AND RATE OF APPLICATION

Apply Red Cement with serrated trowel at approximate rate of 20 sq. ft. per gallon. Area to be coated must be clean and dry. All loose particles should be wire brushed from the surface. It is recommended that the surface to be treated be primed first with BULLDOG Q.D. Primer. Use BULLDOG Red Cement directly from the container without heating or thinning. To combat unusual water conditions or surface cracking imbed a layer of BULLDOG Asphalt Saturated Cotton Fabric in the first coat and then apply second coat. In winter months store inside at 70° F for 24 hours prior to use. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING. FOR EXTERIOR USE ONLY.

| CONTAINER SIZE | APPROXIMATE SHIPPING WEIGHTS |
|----------------------------|------------------------------|
| 5 Gallon Pail | 50 POUNDS |
| 1 Gallon Can (6 to carton) | 60 POUNDS |

TYPICAL PHYSICAL CHARACTERISTICS

| | |
|--|--|
| Nonvolatile Matter, % Solids by Weight | 74.0 |
| Volatile Solvent, % by Weight | 26.0 |
| Mineral Filler, and/or other Stabilizers, Pigments, % by Weight | 28.0 |
| Asphalt Solids, % by Volume | 50.0 |
| Water Content, % by Volume | 0.5 |
| Net Weight Per Gallon, Pounds | 9.1 |
| Dry Film Thickness Without Absorption Applied at Rate of 20 Square Feet Per Gallon | 60 Mills |
| Dry Time @ Recommended Rate of Application | 6-8 Hours Touch, 48 Hrs. Firm |
| Service Temperature | -30°F to +150°F |
| Behavior @ 60°C., ASTM D 4586 | No Sagging, No Blistering |
| Flash Point, in Degrees F., C.C., ASTM D 93 | 104 |
| Condition in Container | Homogeneous, Slight Stirring Required |
| Clean Up of Tools | Use Mineral Spirits or #99 BULLDOG Asphalt Remover |

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
196 WEST 5TH ST
P.O. BOX 58
BAYONNE, NJ 07002
PHONE (201) 339-0855
FAX (201) 339-8320
www.palmerasphalt.com