

#44AF BULLDOG® BITUSTATIC COMPOUND



DESCRIPTION

BULLDOG Bitustatic Compound is composed of high grade asphalt, petroleum solvent blended in with select mineral fillers and other ingredients. It forms a tough film for protection against the elements and will dry to touch in a few hours with a full cure in approximately 24 hours. Bitustatic Compound can be coated with BULLDOG Aluminum Coating after a minimum of 30 days.

USES

BULLDOG Bitustatic Compound is used primarily for dampproofing exterior walls, flashings and parapets and for relining metal or wood gutters or for embedding slate tiles. THIS PRODUCT IS FOR EXTERIOR USE ONLY .

METHODS AND RATE OF APPLICATION

Use a trowel to apply to clean, dry surface at rate of approximately 1/8 inch (3.2mm.) thickness. One gallon (3.78 liters) will cover 13 sq. ft. (1.2M²). Be certain that existing loose paint, loose cement, etc. is wire brushed from the surface. It is recommended that the surface to be treated be primed first with either BULLDOG Q.D. Primer or BULLDOG Asphalt Primer. For unusual water conditions or cracking due to vibration, a layer of BULLDOG Asphalt Saturated Cotton Fabric may be imbedded in BULLDOG Bitustatic Compound with a second trowel coat of the same material applied over the fabric.

COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

| CONTAINER SIZE | APPROXIMATE SHIPPING WEIGHTS |
|----------------|------------------------------|
| 5 Gallon Pail | 46 POUNDS |

TYPICAL PHYSICAL CHARACTERISTICS

| | |
|---|--|
| Nonvolatile Matter, % Solids by Weight | 71.0 |
| Volatile Solvent, % by Weight..... | 29.0 |
| Mineral Filler, % by Weight..... | 20.0 |
| Asphalt Solids, % by Volume..... | 51.0 |
| Water Content, % by Volume | 0.5 |
| Net Weight Per Gallon, Pounds | 8.6 |
| Dry Film Thickness Without Absorption Applied at Rate of 13 Square Feet Per Gallon..... | 77 MILS |
| Dry Time @ Recommended Rate of Application | 24 Hours - Outside Shell |
| Service Temperature | -30°F to +150°F |
| Behavior @ 60°C., ASTM D 4586 | No Sagging, No Blistering |
| Behavior @ 0°C., ASTM D 4586 | No Cracking, No Separation |
| Flash Point, in Degrees F., C.C., ASTM D 93 | 104 |
| Condition in Container..... | Homogeneous |
| Clean Up of Tools..... | Use Mineral Spirits or #99 BULLDOG Asphalt Remover |

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
196 WEST 5TH ST
P.O. BOX 58
BAYONNE, NJ 07002
PHONE (201) 339-0855
FAX (201) 339-8320
www.palmerasphalt.com