

## #601AF BULLDOG® MASTIC DAMPPROOFING CEMENT



### DESCRIPTION

A heavy trowel consistency solvent type mastic designed for sag resistant application to vertical masonry surfaces.  
 SPECIFICATIONS: ASTM D 4586, Type I, Class I

### USES

Affords excellent dampproofing protection by preventing moisture infiltration through surfaces it is applied to. Used on exterior surfaces below grade. Used as a backup for stone and masonry surfaces. Demonstrates excellent adhesion when applied to concrete, masonry and steel surfaces. May be used as a base and surface compound in which reinforcing membrane is embedded. This product will impart a highly resistant dampproofing barrier when applied in accordance with manufacturer's Instructions and using good application practices. It is recommended that BULLDOG Asphalt Primer be used prior to application.

### METHODS AND RATE OF APPLICATION

Apply 1/8" thick with a trowel to clean, dry surface at approximate rate of one gallon (3.78 liters) per 13 square feet (1.2 square meters). For unusual water condition and to help mitigate cracking of surface applied to embed BULLDOG Asphalt Saturated Cotton Fabric and then apply second trowel coat of same material over the fabric. Wait 48 hours before backfilling when applied below grade. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drums	512 POUNDS
5 Gallon Pail	46 POUNDS

### TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight .....	78.0
Volatile Solvent, % by Weight .....	22.0
Mineral Filler and/or other Stabilizer, % by Weight .....	18.0
Asphalt Solids, % by Volume .....	61.5
Water Content, % by Volume .....	0.05
Net Weight Per Gallon, Pounds .....	8.7
Dry Film Thickness Without Absorption Applied at Rate of 13 Square Feet Per Gallon .....	77 Mills
Dry Time @ Recommended Rate of Application .....	3 Days - Outside Shell
Service Temperature .....	-30°F to +150°F
Behavior @ 60°C., ASTM D 4586 .....	No Sagging, No Blistering
Behavior @ 0°C., ASTM D 4586 .....	No Cracking, No Separation
Flash Point, in Degrees F., C.C., ASTM D 93 .....	104 Minimum
Condition in Container .....	Homogeneous
Clean Up of Tools .....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

**The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.**

**DISCLAIMER OF WARRANTIES.** The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY  
 196 WEST 5TH ST  
 P.O. BOX 58  
 BAYONNE, NJ 07002  
 PHONE (201) 339-0855  
 FAX (201) 339-8320  
[www.palmerasphalt.com](http://www.palmerasphalt.com)