

#326 BULLDOG® HEAVY DUTY POLYESTER MAT



DESCRIPTION

Contains 2.1 pounds of polyester per 100 sq. ft. Comes in rolls 40 in. wide by 324 ft. long. A very strong and flexible premium grade reinforcing mat that provides an effective way to resurface smooth surfaced asphalt roofs. Adds less weight to the structure supporting the roof than conventional re-roofing systems and is easier to maintain.

USES

Use with cold process asphalt solvent type coatings or emulsions for resurfacing existing roof. Depending on type of coating used, application can take place at any time of year. Used with Fibered Aluminum Coating as surface treatment, the user can expect years of service from this resurfacing system. This system is designed for use on roofs having an asphalt base and is not designed for other types of roof surface.

METHODS AND RATE OF APPLICATION

Use on clean, sound surface. Apply BULLDOG Asphalt Primer and allow to dry. Apply first coat using BULLDOG Cold Process Coating or BULLDOG Emulsion Roof Coating at rate of 3 gal./100 sq. ft. and embed mat while wet. Then apply a second coat at rate of 4 gal./100 sq. ft. to top of mat. After top coat weathers appropriate time, 3 months for Cold Process Coating and 10 days for Emulsion Roof Coating, apply BULLDOG Fibered Aluminum Coating or BULLDOG/DUREX White Elastomeric Coating. Each roll is individually wrapped in a polyethylene bag. One roll with 3 inch side laps and 6 inch end laps covers 1000 square feet.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
One Roll	30 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Tensile Strength, MD, ASTM D 1682	75 Pounds
CD, ASTM D 1682	100 Pounds
Elongation MD, ASTM D 1682.....	55
CD, ASTM D 1682.....	55
Tear Strength, MD, ASTM D 2263	20 Pounds
CD, ASTM D 2263	30 Pounds
Weight of Polyester Per 100 Square Feet.....	2.1 Pounds

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE(201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com